







MATT CLEAR KIT (2:1)

<p>Product Description: 2K high quality acrylic clear coat for professional repair to surfaces requiring a matt finish. Excellent matt appearance with a durable, hard finish. Very smooth levelling. The VOC content of the mixture is 593.7 g/l. The amount of VOC is below 840g/l. Therefore these products meet EU directive (2004/42/EC) that sets the VOC level for this product category (E) as 840</p>
<p>Technical Characteristics: Matt Clear can be applied over base coats and existing coatings. Existing paintwork should first be sanded and cleaned with a silicone remover. For dulling the colour it is recommended to use the following: Grey unwoven abrasive fabric with a dulling paste. Abrasive paper grade 600-800 (for dulling on wet). Abrasive paper graded 360-400 (for dulling by machine). DO NOT POLISH</p>
<p>Pre- Treatment: Must be applied on a thoroughly degreased substrate</p>

 <p>Mixing Ratio</p>	<p><u>For Full Matt</u> Matt Clear 2 parts by volume Matt Activator 1 part by volume You can use 10% Universal Thinners</p>
 <p>Spray Viscosity</p>	<p>16-18 seconds BSB cup @ 20°C</p>
<p>Pot Life</p>	<p>Approx 7 hours @ 20°C</p>
 <p>Spray guns</p>	<p>Nozzle: gravity 1.3 – 1.4mm Pressure according to manufacturers recommendations.</p>
 <p>Application</p>	<p>Two single layers.</p>
 <p>Drying</p>	<p>Evaporation Time: Between coats: approx. 10 minutes Before Baking: approx. 15 minutes Dust free at 20°C: approx. 15 minutes Baking at 60°C: approx. 30 minutes DO NOT POLISH</p>
 <p>Information</p>	<p>For professional use only. Always consult the MB Coatings Health and Safety data sheets. Always read the risks and precautions stated on the product label.</p>

The information contained in these pages is not intended to be exhaustive, and all persons using the product without first obtaining confirmation for MB Coatings as to the suitability of the product for the intended use, does so at their own risk. Whilst every effort is made to ensure the information given about the product (whether in this sheet or otherwise) is correct, we have no control over the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree to do so, we do not accept any liability arising out of use of the product. All information contained in this sheet is liable to modification from time to time, and we reserve the right to change the product in accordance with our policy of continuous product development. Activators have 6 month shelf life.

MB PRODUCTS (UK) LTD t/a MB COATINGS, UNIT 230 AMPRESS PARK, LYMINGTON, HANTS SO41 8JW

TEL: 01590 677676, FAX: 01590 678578

www.mbcoatings.co.uk