

# 57 COMPLIANT WASSEKLAR CLEAR KIT ( 2:1 )







Product Description: 2K acrylic clear with anti-scratch resin with high gloss retention even when air-dried, excellent durability, resistance to yellowing. Wasseklar can be applied on a solvent or waterborne base coat.

2004/42/IIb(e)(840)(570) The EU limit for this product (category IIB(e)) in ready for use form is max 840 grams of VOC per litre. The VOC content of this product is 570 g/l

Technical Characteristics: 57 has been developed in conjunction with the activator to ensure the solids of the activator and the clear perfectly cross-linked giving a high gloss tough lasting finish and meets the current VOC legislation. Colour: Water Clear

Pre- Treatment:

Must be applied on a thoroughly degreased substrate

 <p>Mixing Ratio</p>	<p>Wasseklar 57 Clearcoat 100 (vol) 100 g            57 HS Activator 50 (vol) 50 g            You can use up to 5% Thinners</p>
 <p>Spray Viscosity Pot Life:</p>	<p>18-22 seconds BSB cup @ 20°C            2 - 2½ hours @ 20°C</p>
 <p>Spray guns</p>	<p>HVLP Gravity feed: 1.2 - 1.4 mm 2 bar</p>
 <p>Application</p>	<p>High Gloss Finish: ¾ or 1 full coat leave 5-10 minutes,            1 full coat (times can vary on application) Total film            build 40-50 microns            Winter: 1 ¾ coat 5 minute flash off 1 full coat</p>
 <p>Drying</p>	<p>Oven 30 minutes @ 60°C polish within an hour            10 - 15 minutes using conventional infra - red</p>
 <p>Information</p>	<p>For professional use only. Always consult the MB Coatings Health and Safety data sheets. Always read the risks and precautions stated on the product label.</p>

The information contained in these pages is not intended to be exhaustive, and all persons using the product without first obtaining confirmation for MB Coatings Ltd as to the suitability of the product for the intended use, does so at their own risk. Whilst every effort is made to ensure the information given about the product (whether in this sheet or otherwise) is correct, we have no control over the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree to do so, we do not accept any liability arising out of use of the product. All information contained in this sheet is liable to modification from time to time, and we reserve the right to change the product in accordance with our policy of continuous product development. All Activators have 12 month shelf life.

**MB COATINGS LTD, UNIT 230 AMPRESS PARK, LYMINGTON, HANTS SO41 8JW**

**TEL: 01590 677676, FAX: 01590 678578**

[www.mbcoatings.co.uk](http://www.mbcoatings.co.uk)